

Technical Data Sheet

Fibracon[®] PTFE + 23% Carbon+ 2% Graphite

PTFE

Typical characteristics

- Good for dry and poorly lubricated environments
- Good thermal conductivity
- Electrically conductive
- Reduced deformation under load compared to virgin PTFE

Typical industries

- 化学处理行业
- 车辆构造
- 电子
- 石油和天然气
- 机械工程行业
- Healthcare
- 食品行业
- 风能

	Test method	Unit	Guideline value
General properties			
Density	ASTM D4894	g / cm ³	2.09
Mechanical properties			
Hardness	Needle	Shore D	64 - 70
Tensile Strength (23°C)	ASTM D4894	MPa	18
Elongation at Break	ASTM D4894	%	65
Thermal properties			
Service Temperature		°C	-200 to +260

This data provides typical values on a small selection of properties of the material and should only be used as a guide to the generic material performance.

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 24/05/2026 • Release: 20/09/2023
 PIM-ID: 709613 • PIM-Code: 44-40-16.3.13.14-9.7.8.5.5.27.5.10-1
 Company-IDs: 21220

Page 1 / 1 (Dates in DD/MM/YYYY)

