

## Technical Data Sheet

# Fibracon<sup>®</sup> PTFE + 60% Bronze

PTFE

### Typical characteristics

- Improved thermal and electrical conductivity
- Reduced chemical resistace
- Reduced deformation under load

### Typical industries

- 化学处理行业
- 车辆构造
- 电子
- 石油和天然气
- 机械工程行业
- Healthcare
- 食品行业
- 风能

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	ASTM D1457	g / cm <sup>3</sup>	3.8 - 4.0
<b>Mechanical properties</b>			
Hardness	ASTM D1706	Shore D	60 - 64
Tensile Strength (23°C)	ASTM D1457	N/mm <sup>2</sup>	>12
Elongation at Break	ASTM D1457*	%	>80
<b>Thermal properties</b>			
Service Temperature		°C	-200 to +260

\*12mm initial gauge used. This data provides typical values on a small selection of properties of the material and should only be used as a guide to the generic material performance.

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 24/05/2026 • Release: 20/09/2023  
 PIM-ID: 709626 • PIM-Code: 36-40-16.13.14-9.7.8.5.5.27.5.10-2  
 Company-IDs: 21220

Page 1 / 1 (Dates in DD/MM/YYYY)

