

Technical Data Sheet

Durostone[®] EPC 203

GFK-EP

Typical characteristics

- Good mechanical properties
- Good electrical properties
- Epoxy (EP) resin matrix reinforced with an e-glass fine fabric

Typical industries

- 发电机和电机
- 油浸式变压器
- 干式变压器
- 电气行业
- 电气绝缘元件

| | Test method | Unit | Guideline value |
|--|-------------|---------------------|----------------------|
| Mechanical properties | | | |
| Density | ISO 1183 | g / cm ³ | 1,85 |
| Flexural strength [⊥] | ISO 178 | MPa | 450 |
| Flexural strength [⊥] +150°C | ISO 178 | MPa | 230 |
| Modulus of elasticity in flexion [⊥] | ISO 178 | MPa | 23000 |
| Modulus of elasticity in flexion [⊥] +150°C | ISO 178 | MPa | 18000 |
| Compressive strength [⊥] | ISO 604 | MPa | 500 |
| Tensile strength II | ISO 527 | MPa | 350 |
| Impact strength II (Charpy) | ISO 179 | kJ / m ² | 100 |
| Thermal properties | | | |
| Temperature index | IEC 60216 | T.I. | 155 |
| Insulation class | IEC 60085 | / | F |
| Physical properties | | | |
| Water absorption (4mm thickness) | ISO 62 | % | 0,1 |
| Dielectrical properties | | | |
| Electric strength 90°C under oil [⊥] | IEC 60243 | kV / mm | 16 |
| Electric strength 90°C under oil II | IEC 60243 | kV/25mm | 70 |
| Insulation resistance | IEC 60167 | Ω | 10 ¹⁴ |
| Specific surface resistance | IEC 60093 | Ω | 5 x 10 ¹⁰ |
| Comparative tracking index | IEC 60112 | CTI | 180 |

ri-inquiry@roechling.com • www.roechling.com/industrial/materials



| | Test method | Unit | Guideline value |
|--|-------------|----------|-----------------|
| Insulation resistance after 24 h water immersion | IEC 60167 | Ω | 10^{12} |

⊥ = perpendicular to the lamination || = parallel to the lamination

The data stated above are average values verified on the basis of regular statistical tests and controls. All information in this publication is based on current technical knowledge and experience. Due to the large number of possible influences during processing and application, it does not exempt the user/processor from carrying out their own tests and trials. Responsibility for the evaluation of the end product for the intended use and compliance with the applicable relevant legal requirements lies exclusively with the user/processor as well as the distributor of the respective product/end product. Suggested uses do not constitute an assurance of suitability for the recommended purpose. The information in this publication and our declarations in connection with this publication do not constitute acceptance of a guaranteed or warranted characteristic. Guarantee declarations require our separate express written declaration in order to be effective. We reserve the right to adapt the product to technical progress and new developments. The products described in this publication are only sold to customers with the appropriate expertise and not to consumers. Please do not hesitate to contact us if you have any questions or if you experience any specific application problems. If the application for which our products are used is subject to an official approval requirement, the user/processor is responsible for obtaining these approvals. Our application recommendations do not exempt the user/processor from the obligation to examine and, if necessary, clarify the possibility of infringements of third-party rights. In all other respects, we refer to our General Terms and Conditions (GTC). These are available at: www.roechling-industrial.com/gtc



ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 25/05/2026 • Release: 20/09/2023
 PIM-ID: 710087 • PIM-Code: 1112-19-17.10.14-4.6.6.11.7-13
 Company-IDs: 21020

Page 2 / 2 (Dates in DD/MM/YYYY)

