

## Technical Data Sheet

# Fibracon<sup>®</sup> PTFE + 10% Carbon Fibre

PTFE

### Typical characteristics

- Low wear when lubricated with water
- Reduced deformation under load (improved compressive strength)
- Improved thermal and electrical conductivity

### Typical industries

- 化学处理行业
- 车辆构造
- 电子
- 石油和天然气
- 机械工程行业
- Healthcare
- 食品行业
- 风能

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	ASTM D1457	g / cm <sup>3</sup>	2.0 - 2.2
<b>Mechanical properties</b>			
Hardness	ASTM D1706	Shore D	56 - 61
Tensile Strength (23°C)	ASTM D1457	N/mm <sup>2</sup>	>18
Elongation at Break	ASTM D1457*	%	>300
<b>Thermal properties</b>			
Service Temperature		°C	-200 to +260

\*12mm initial gauge used. This data provides typical values on a small selection of properties of the material and should only be used as a guide to the generic material performance.

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

