

Technical Data Sheet

Polystone[®] M MDT blue

PE-UHMW / PE 1000

Typical characteristics

- Metal detectable
- High abrasion resistance
- Good sliding properties
- Low coefficient of friction
- High impact resistance

Typical industries

- 食品行业
- 肉类、鱼类和禽类加工

| | Test method | Unit | Guideline value |
|---|-------------------|-----------------------|-------------------|
| General properties | | | |
| Density | DIN EN ISO 1183-1 | g / cm ³ | >1,0 |
| Water absorption | DIN EN ISO 62 | % | 0,05 |
| Flammability (Thickness 3 mm / 6 mm) | UL 94 | | HB |
| Molecular weight | - | 10 ⁶ g/mol | ~ 9 |
| Mechanical properties | | | |
| Yield stress | DIN EN ISO 527 | MPa | >19 |
| Elongation at break | DIN EN ISO 527 | % | >50 |
| Tensile modulus of elasticity | DIN EN ISO 527 | MPa | >600 |
| Shore hardness | DIN EN ISO 868 | scale D | >63 |
| Thermal properties | | | |
| Melting temperature | ISO 11357-3 | °C | 130 ... 135 |
| Coefficient of linear thermal expansion | DIN 53752 | 10 ⁻⁶ / K | 150 ... 230 |
| Service temperature, long term | Average | °C | -200 ... 80 |
| Service temperature, short term (max.) | Average | °C | 130 |
| Electrical properties | | | |
| Volume resistivity | DIN EN 62631-3-1 | Ω * cm | >10 ¹⁴ |
| Surface resistivity | DIN EN 62631-3-2 | Ω | >10 ¹⁴ |

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

