

Technical Data Sheet

Fibracon[®] PTFE + Anti-Static Filler

Typical characteristics

- Addition of carbon gives anti-static properties to the material
- Grades are available where the raw material has been approved to FDA standards

Typical industries

- 化学处理行业
- 车辆构造
- 电子
- 石油和天然气
- 机械工程行业
- Healthcare
- 食品行业
- 风能

	Test method	Unit	Guideline value
General properties			
Density	ASTM D4894	g / cm ³	2.15
Mechanical properties			
Hardness	Needle	Shore D	56
Tensile Strength (23°C)	ASTM D4894	MPa	>20
Elongation at Break	ASTM D4894	%	250
Thermal properties			
Service Temperature		°C	-200 to +260

This data provides typical values on a small selection of properties of the material and should only be used as a guide to the generic material performance.

Röchling Industrial (UK) Ltd. – High Peak

Bowden Hey Road - Chapel-en-le-Frith • SK23 0QZ High Peak, Derbyshire/United Kingdom (GB) • Tel. +44 1298 811 800
info@roechling-fibracon.co.uk • www.roechling.com/industrial/high-peak

Print: 04/05/2024 • Release: 20/09/2023

PIM-Version: 33 • PIM-ID: 709628 • PIM-Code: 33-40-11.8-7.6.8.5.9.5.10-1

