

## Technical Data Sheet

# Fibracon<sup>®</sup> PTFE virgin

### Typical characteristics

- Wide operating temperature - 200°C to +260°C
- Exceptionally low co-efficient of friction
- Chemical resistance

### Typical industries

- 化学处理行业
- 车辆构造
- 电子
- 石油和天然气
- 机械工程行业
- Healthcare
- 食品行业
- 运动与休闲
- 风能
- Semiconductor Front-End Wet Bench
- Semiconductor Front-End applications

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	ASTM D4894	g / cm <sup>3</sup>	2.17
<b>Mechanical properties</b>			
Hardness	Needle	Shore D	54 - 60
Tensile Strength (23°C)	ASTM D4894	N/mm <sup>2</sup>	25
Elongation at Break	ASTM D4894	%	250
<b>Thermal properties</b>			
Service Temperature		°C	-200 to +260

This data provides typical values on a small selection of properties of the material and should only be used as a guide to the generic material performance.

#### Röchling Industrial (UK) Ltd. – High Peak

Bowden Hey Road - Chapel-en-le-Frith • SK23 0QZ High Peak, Derbyshire/United Kingdom (GB) • Tel. +44 1298 811 800  
 info@roechling-fibracon.co.uk • www.roechling.com/industrial/high-peak

Print: 04/05/2024 • Release: 20/09/2023

PIM-Version: 49 • PIM-ID: 709600 • PIM-Code: 49-40-9.11.27-7.6.8.5.5.9.5.3.10.9.10-1

