

Technical Data Sheet

Glastic® CBC-503

Typical characteristics

- Electrostatic discharge safe, optically sensible
- Dimensionally Stable

Typical industries

- 电子

	Test method	Unit	Guideline value
General properties			
Standard Color			Light Gray
Chemical Resistance			Very Good
Mechanical properties			
Flexural Strength	ASTM D 790	psi	55,000
IZOD Impact Strength (notched)	ASTM D 256	ft. lb./in.	15
Thermal properties			
Thermal Conductivity	ASTM C 177		2.0
Coefficient of Thermal Expansion, parallel	ASTM D 696	10 ⁻⁶ K ⁻¹	7.1
Coefficient of Thermal Expansion, perpindicular	ASTM D 696	10 ⁻⁶ K ⁻¹	20.5
Glass Transition Temperature, T _g	ASTM E 1356	°F	345
Thermal Decomposition Temperature @1% loss	ASTM E 1641	°F	440
Thermal Decomposition Temperature @5% loss	ASTM E 1641	°F	550
Thermal Decomposition Temperature @10% loss	ASTM E 1641	°F	622
Max Surface Operating Temperature		°F	572
Solder Heat Resistance 10 min. @500°F			Pass
Flame resistance properties			
UL Subject 94	UL 94		HB
Physical properties			
Water Absorption	ASTM D 570	% by wt.	<0.2
Specific Gravity	ASTM D 792		1.84
Barcol Hardness	ASTM D 2583		77

Röchling Industrial Cleveland, LP

4321 Glenridge Road • 44121 Cleveland/United States (US) • Tel. +1 216 486-0100
 info@glastic.com • www.roechling.com/cleveland

Print: 13/05/2024 • Release: 20/09/2023 • Version: 1.0
 PIM-Version: 37 • PIM-ID: 715311 • PIM-Code: 37-23-7.7-8-6



	Test method	Unit	Guideline value
ESD properties			
Surface Resistivity	ASTM D 4496	Ω/square	10 ⁵ - 10 ⁹
Volume Resistivity	ASTM D 4496	Ω/square	10 ⁵ - 10 ⁹
ESD Safe			Yes

All of the information, suggestions, and recommendations pertaining to the properties and uses of the Röchling Glastic Composites products described herein are based upon tests and data believed to be accurate; however, the final determination regarding the suitability of any material described herein for the use contemplated, the manner of such use, and whether the use infringes any patents is the sole responsibility of the user. THERE IS NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Under no circumstances shall we be liable for incidental or consequential loss or damage. Glastic® is a registered trademark of Röchling Glastic Composites. UL® is a registered trademark of Underwriters Laboratories, Inc.

