

Technical Data Sheet

Glastic® UTS 1478

Typical characteristics

- NEMA GPO-2
- High Strength
- Flame-Resistant Meets UL94 VO

Typical industries

- 开关设备
- 电气行业
- 电气绝缘元件
- 电子

	Test method	Unit	Guideline value
General properties			
Part Number			1478
NEMA Grade LI 1-1989	NEMA LI-1		GPO-2/GPO-2P
Standard Color			Red
UL Temperature Index - Electrical	UL 746B	°C	130
UL Temperature Index - Mechanical	UL 746B	°C	160
UL Recognition File Number			E81928
Mechanical properties			
Flexural Strength	ASTM D 790	psi	24,600
Flexural Strength @130°C	ASTM D 790	psi	14,900
Compressive Strength	ASTM D 695	psi	39,000
Tensile Strength	ASTM D 638	psi	8,900
IZOD Impact Strength (notched)	ASTM D 256	ft. lb./in.	10.7
Shear Strength	ASTM D 732	psi	13,400
Thermal properties			
Coefficient of Thermal Expansion	ASTM D 696	(in./in.°C) x 10-5	2
Thermal Conductivity	ASTM C 177		1.8
Flame resistance properties			
UL Subject 94	UL 94		V0
UL Hot Wire Ignition	UL 746A	sec.	300+
UL High Amp Ignition	UL 746A		200+
Ignition Time		sec.	81



	Test method	Unit	Guideline value
Burn Time		sec.	48
Oxygen Index	ASTM D 2863	%O ₂	36
Physical properties			
Water Absorption	ASTM D 570	% by wt.	0.6
Specific Gravity	ASTM D 792		1.8
Dielectrical properties			
Electrical Strength - Perpendicular S/T in Air	ASTM D 149	Vpm	433
Electrical Strength - Perpendicular S/T in Oil	ASTM D 149	Vpm	567
Electrical Strength - Parallel S/S in Oil	ASTM D 149	kV	51
Arc Resistance	ASTM D 495	sec.	130
IEC Track Resistance (CTI)	UL 746A	V	600+
Permittivity, 60 Hz	ASTM D 150		4.1
Dissipation Factor, 60 Hz	ASTM D 150		0.011
Dissipation Factor, MHz	ASTM D 150		0.10
Permittivity, MHz	ASTM D 150		3.9
Insulation Resistance	ASTM D 257	Ω x 10 ¹²	270

All of the information, suggestions, and recommendations pertaining to the properties and uses of the Röchling Glastic Composites products described herein are based upon tests and data believed to be accurate; however, the final determination regarding the suitability of any material described herein for the use contemplated, the manner of such use, and whether the use infringes any patents is the sole responsibility of the user. THERE IS NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Under no circumstances shall we be liable for incidental or consequential loss or damage. Glastic® is a registered trademark of Röchling Glastic Composites. UL® is a registered trademark of Underwriters Laboratories, Inc.

