

Technical Data Sheet

Matrox[®] EX 60 black extruded

PE-UHMW / PE 1000

Typical characteristics

- Low coefficient of friction
- Good wear properties
- Antistatic

Typical industries

- 散装材料搬运

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	>0,99
Water absorption	DIN EN ISO 62	%	<0,01
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
Molecular weight	-	10 ⁶ g/mol	~ 9
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	>20
Elongation at break	DIN EN ISO 527	%	>50
Tensile modulus of elasticity	DIN EN ISO 527	MPa	>900
Notched impact strength	DIN EN ISO 11542-2	kJ / m ²	>40
Shore hardness	DIN EN ISO 868	scale D	>63
Wear resistance	Sand-slurry		100
Sand Slurry	1018 Steel=10		~ 100
Thermal properties			
Melting temperature	ISO 11357-3	°C	130 ... 135
Thermal conductivity	DIN 52612-1	W / (m * K)	0,41
Thermal capacity	DIN 52612	kJ / (kg * K)	1,90
Coefficient of linear thermal expansion	DIN 53752	10 ⁻⁶ / K	150 ... 230
Service temperature, long term	Average	°C	-200 ... 80
Service temperature, short term (max.)	Average	°C	130
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	79
Electrical properties			

ri-inquiry@roebling.com • www.roebling.com/industrial/materials

Print: 09/05/2025 • Release: 11/12/2024 • Version: 2.0
 PIM-Version: 777 • PIM-ID: 591136 • PIM-Code: 777-41-12.126.16-6-5
 Company-IDs: 20000-1

Page 1 / 2 (Dates in DD/MM/YYYY)



	Test method	Unit	Guideline value
Volume resistivity	DIN EN 62631-3-1	$\Omega \cdot \text{cm}$	$<10^9$
Surface resistivity	DIN EN 62631-3-2	Ω	$<10^9$

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 09/05/2025 • Release: 11/12/2024 • Version: 2.0
PIM-Version: 777 • PIM-ID: 591136 • PIM-Code: 777-41-12.126.16-6-5
Company-IDs: 20000-1

