

Technical Data Sheet

Polystone® P CubX® (Copolymer) PG + UV-stabilized white

PP-C

Typical characteristics

- High longitudinal and transversal stiffness
- Good handling
- Low weight
- Good thermal insulation
- Good machinability
- Good weldability
- Chemical resistant
- UV-resistant

Typical industries

- 运动与休闲
- 饮用水和废水技术
- 化工储罐
- 游泳池塑膠床單

	Test method	Unit	Guideline value
Properties for the full cross-ribbed twin-wall sheet			
Thermal conductivity	ISO 8302 Tested with: GHP 500-1, Single-sheet process	W / (m * K)	Lambda 0,14
Density	DIN EN ISO 1183	g / cm ³	0,3
Area weight		kg/m ²	17,1
Weld strength lattice / covering sheets		MPa	≥ 20
Flatness	DIN EN ISO 15860	mm/m	≤ 3
Water absorption	DIN EN ISO 62	%	< 0,1
Properties for the covering sheets			
Density, RT	DIN EN ISO 1183	g / cm ³	0,92
Yield stress	DIN EN ISO 527	MPa	24
Elongation at break	DIN EN ISO 527	%	> 50
Tensile modulus of elasticity	DIN EN ISO 527	MPa	1200
Notched impact strength	DIN EN ISO 179	kJ / m ²	> 30

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 24/05/2025 • Release: 05/05/2025 • Version: 2.0
PIM-Version: 822 • PIM-ID: 710120 • PIM-Code: 822-5-11.20.14.11.70.16.33.15-3.6.7.8-5
Company-IDs: 20000-1

Page 1 / 2 (Dates in DD/MM/YYYY)



The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 24/05/2025 • Release: 05/05/2025 • Version: 2.0
PIM-Version: 822 • PIM-ID: 710120 • PIM-Code: 822-5-11.20.14.11.70.16.33.15-3.6.7.8-5
Company-IDs: 20000-1

Page 2 / 2 (Dates in DD/MM/YYYY)

