

Technical Data Sheet

Polystone[®] P MG - ASTM

Typical industries

- Healthcare
- 生命科學
- 製藥

	Test method	Unit	Guideline value
General properties			
Density	ASTM D792	g / cm ³	0.91
Water Absorption	ASTM D570	%	<0.1
Mechanical properties			
Hardness	ASTM D2240	Shore D	72
Tensile Strength at yield 73°F	ASTM D638	psi	4900
Elongation at Break	ASTM D638	%	>400
Flexural Strength	ASTM D790	psi	200000
Izod Impact, Notched	ASTM D256	ft-lb/in	1.0
Coefficient of Friction, Dynamic			0.25-0.28
Thermal properties			
CTE, linear	ASTM D696	in/in/°F	6x10 ⁻⁵
Melting Point		°F	323
Maximum Service Temperature, Air		°F	180
Heat Deflection Temperature 264psi	ASTM D648	°F	210
Flammability, UL94		1/8 inch	HB
Electrical properties			
Surface resistivity	ASTM D257	Ohm/cm	>10 ¹⁴
Compliance properties			
FDA			Yes
USP Class VI	ASTM Certified		Yes

Röchling Industrial Gastonia, LP

903 Gastonia Technology Parkway • 28034 Dallas/United States (US) • Tel. +1 704 922-7814
 rep@roechling-plastics.us • www.roechling.com/industrial/rep-us

Print: 09/05/2024 • Release: 26/01/2024 • Version: 2.0
 PIM-Version: 42 • PIM-ID: 717953 • PIM-Code: 42-21-9.9.8-2



The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

