

Technical Data Sheet

Trovidur[®] ESV-EX

PVC-U

Typical characteristics

- High impact resistance
- UV-resistant
- Weatherability
- Good stretching properties for thermoforming
- RoHS compliant
- ELV compliant
- WEEE compliant
- RLAP compliant
- High cold impact strength
- Good surface quality
- Flame retardant
- Self-Extinguishing after removal of the flame
- Good vacuum forming properties

Typical industries

- 建筑行业

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	1,41
Water absorption	DIN EN ISO 62	%	0,20
Flammability (Thickness 1,5 mm)	BS 476 Part 7 (GB)		Class 1
VOC	ISO 16.000	conform	A+
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	45
Elongation at break	DIN EN ISO 527	%	20
Tensile modulus of elasticity	DIN EN ISO 527	MPa	2500
Notched impact strength	DIN EN ISO 179	kJ / m ²	8
Shore hardness	DIN EN ISO 868	scale D	80
Ball Hardness	ISO 2039	MPa	100
Compressive strength	DIN EN ISO 604	MPa	65

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 01/05/2025 • Release: 20/09/2023 • Version: 2.0
 PIM-Version: 750 • PIM-ID: 591095 • PIM-Code: 750-14-18.15.9.18.14.16.15.16.11.19.14.11.11-10-2
 Company-IDs: 20000-2

Page 1 / 2 (Dates in DD/MM/YYYY)



	Test method	Unit	Guideline value
Bending strength	DIN EN ISO 178	MPa	60
Thermal properties			
Thermal conductivity	DIN 52612-1	W / (m * K)	0,16
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	76
Service Temperature		°C	-20 ... +60
Heat deflection temperature	DIN EN ISO 75	°C	70
Coefficient of linear thermal expansion	DIN EN ISO 11359-2	mm/m K	~ 0,075
Electrical properties			
Dielectric constant	IEC 60250		3,2
Dielectric dissipation factor (10 ⁶ Hz)	IEC 60250		0,02
Volume resistivity	DIN EN 62631-3-1	Ω * cm	>10 ¹⁵
Surface resistivity	DIN EN 62631-3-2	Ω	>10 ¹³

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale. Information on the REACH regulation can be found in our Product Handling Information Sheets, in our REACH information letter as well as in the SCIP database.

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 01/05/2025 • Release: 20/09/2023 • Version: 2.0
PIM-Version: 750 • PIM-ID: 591095 • PIM-Code: 750-14-18.15.9.18.14.16.15.16.11.19.14.11.11-10-2
Company-IDs: 20000-2

Page 2 / 2 (Dates in DD/MM/YYYY)

