

## Technical Data Sheet

# Trovidur<sup>®</sup> PHT

PVC-C

### Typical characteristics

- Uniform physical properties
- Continuous service temperature up to 90 °C
- Good resistance to acids, lyes and salt solutions
- Flame retardant
- Self-Extinguishing after removal of the flame
- Good weldability
- Good thermoformability
- Good glueability
- Good impact strength

### Typical industries

- 化学处理行业
- 化工储罐
- 洁净室技术

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	DIN EN ISO 1183-1	g / cm <sup>3</sup>	1,64
Water absorption	DIN EN ISO 62	%	0,20
<b>Mechanical properties</b>			
Yield stress	DIN EN ISO 527	MPa	60
Elongation at break	DIN EN ISO 527	%	15
Tensile modulus of elasticity	DIN EN ISO 527	MPa	3000
Notched impact strength	DIN EN ISO 179	kJ / m <sup>2</sup>	6
Shore hardness	DIN EN ISO 868	scale D	82
<b>Thermal properties</b>			
Thermal conductivity	DIN 52612-1	W / (m * K)	0,13
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	107
Service Temperature		°C	-10 ... +90
Coefficient of linear thermal expansion	DIN EN ISO 11359-2	mm/m K	~ 0,075
Glow wire ignition temperature	DIN EN 60695-2-13	°C	990

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)



	Test method	Unit	Guideline value
Glow wire flammability index	DIN EN 60695-2-12	°C	960
<b>Electrical properties</b>			
Volume resistivity	DIN EN 62631-3-1	$\Omega \cdot \text{cm}$	$>10^{15}$
Surface resistivity	DIN EN 62631-3-2	$\Omega$	$>10^{13}$

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 20/04/2026 • Release: 20/09/2023 • Version: 1.0  
 PIM-ID: 591021 • PIM-Code: 1101-36-27.11.20.16.11.16.34.3.162-9.7.7-5  
 Company-IDs: 20000-2

Page 2 / 2 (Dates in DD/MM/YYYY)

